

		生效日期 Effective Date	2022-07-14
		版本 Version	3.0

高松厚度单面涂布白卡 IBP

HIGH BULK GCL

检测项目 Items		单位 Unit	检验方法 Standards	偏差 Tolerance	标准 Standard						
定量 Grammage		g/m ²	ISO536	±3%	210	235	250	270	300	325	350
厚度 Thickness		μm	ISO534	±15	305	355	380	410	460	510	560
泰伯挺度 Taber Stiffness	纵向 MD	mN·m	ISO2493	±15%	8.0	11.5	14.5	17.5	23.5	29.5	34.0
	横向 CD	mN·m		±15%	4.0	5.0	7.0	8.5	11.0	14.5	16.5
水分 Moisture		%	ISO287	±1.0	7.5						
PPS 表面粗糙度 Surface Roughness		μm	ISO8791-4	≤	1.6						
亮度 Brightness (D65/10)	正面 Top	%	ISO2470-2	±3	90.0						
	背面 BACK				85.0						
光泽度 75° Gloss		%	ISO8254	≥	40						
表面强度 IGT Picking		m/s	ISO3783	≥	1.3						
层间结合强度 Ply Bond		J/m ²	TAPPI569	≥	130						
正面吸水 Cobb (60s)		g/m ²	ISO535	≤	TOP/BACK: 40						

检测条件 Testing Condition:

【FOR EXPORT】

温度 Temperature: ① (23±1) °C/相对湿度 Relative Humidity: (50±2) %



- | | |
|------------|-------------------------|
| ① 正面三道刮刀涂布 | Surface blade coated |
| ② 面层 | Top Layer, LBKP+NBKP |
| ③ 芯层 | Middle Layer, BCTMP |
| ④ 底层 | Bottom Layer, LBKP+NBKP |
| ⑤ 背面一道刮刀涂布 | Back blade coated |

产品特点 Product Characteristics:

高松厚度社会卡, 挺度高, 平整性好, 轻量化, 普通包装用途, 适合高速胶印。 High Thickness and Stiffness, good flatness, Lightweight, general box packaging purpose, can be fit for high-speed offset.